



# FRAGRANTE



*Croccante, fresco, variegato come i pani appena sfornati, in questo frassino sbiancato scie di tortora, nocciola e crema si alternano come nastri distesi su un piano, in un luminoso gioco tra chiari e scuri.*

## Caratteristiche tecniche

|                                    |                           |
|------------------------------------|---------------------------|
| <b>Legno</b>                       | Frassino olivato          |
| <b>Spessore</b>                    | 15 mm                     |
|                                    | Sp. lamella nobile 3,6 mm |
| <b>Larghezza</b>                   | 158\192 mm                |
| <b>Lunghezza</b>                   | 1850\2000\2400 mm         |
|                                    | secondo disponibilità     |
| <b>Scelta</b>                      | Unica                     |
| <b>Retro</b>                       | Abete\Latifoglia          |
| <b>Provenienza</b>                 | Comunità Europea          |
| <b>Classe di reazione al fuoco</b> | Cfl-s1                    |
| <b>Emissione formaldeide</b>       | E1 (<0,1ppm)              |
| <b>Conduttività</b>                | 0,14 W/mK                 |
| <b>Resistenza termica</b>          | 0,10 K/W                  |
| <b>Peso</b>                        | 8,7 Kg/mq                 |
| <b>Umidità</b>                     | 7%+ / -2%                 |
| <b>Durezza</b>                     | 28-40 N/mm <sup>2</sup>   |



# FRAGRANTE



*Crunchy, fresh and variegated like bread just taken out from oven. In this whitened ash, dove-grey, hazel and cream wakes alternate like ribbons laid on a flat surface, in a shining game of lights and shades.*

## Technical specific

|                       |                           |
|-----------------------|---------------------------|
| Wood                  | Olive ash                 |
| Thickness             | 15 mm                     |
|                       | Th. top layer 3,6 mm      |
| Width                 | 158\192 mm                |
| Length                | 1850\2000\2400 mm         |
|                       | according to availability |
| Selection             | Unique                    |
| Back                  | Spruce                    |
| Origin                | European Union            |
| Fire resistance class | Cfl-s1                    |
| Formaldehyde emission | E1 (<0,1ppm)              |
| Conductivity          | 0,14 W/mK                 |
| Thermal resistance    | 0,10 K/W                  |
| Weight                | 8,7 Kg/mq                 |
| Humidity              | 7%+ / -2%                 |
| Hardness              | 28-40 N/mm²               |

