

# FIOR DI TÈ




*Questo teak ha in sé i colori e i movimenti del tè nero birmano in infusione, una base aranciata e calda, rosata dalla leggera sbiancatura, in cui si sciolgono, tra onde voluttuose e fili sottili, striature più scure e profonde.*

## Caratteristiche tecniche

<b>Legno</b>	Teak Burma
<b>Spessore</b>	15 mm
	Sp. lamella nobile 4 mm
<b>Larghezza</b>	Multilarghezza*
<b>Lunghezza</b>	da 700 a 3000 mm
<b>Scelta</b>	Senza nodi
<b>Retro</b>	Abete
<b>Provenienza</b>	Myanmar (Birmania)
<b>Classe di reazione al fuoco</b>	Cfl-s1
<b>Emissione formaldeide</b>	E1 (<0,1ppm)
<b>Conduktività</b>	0,14 W/mK
<b>Resistenza termica</b>	0,10 K/W
<b>Peso</b>	9 Kg/mq
<b>Umidità</b>	10%+ / -2%
<b>Durezza</b>	35 N/mm <sup>2</sup>

\*Multilarghezza: dalle 3 alle 5 larghezze miste, comprese tra 100 mm e 300 mm, a seconda di quantità e disponibilità



# FIOR DI TÈ



*This teak presents the colours and the movements of an infusion of Burmese black tea: an orange and warm base, rosy and slightly bleached where darker and deeper streaks melt among voluptuous waves and thin filaments.*

## Technical specific

<b>Wood</b>	Burma teak
<b>Thickness</b>	15 mm
	Th.top layer 4 mm
<b>Width</b>	Multi-width*
<b>Length</b>	from 700 to 3000 mm
<b>Selection</b>	Knot-free
<b>Back</b>	Spruce
<b>Origin</b>	Myanmar (Burma)
<b>Fire resistance class</b>	Cfl-s1
<b>Formaldehyde emission</b>	E1 (<0,1ppm)
<b>Conductivity</b>	0,14 W/mK
<b>Thermal resistance</b>	0,10 K/W
<b>Weight</b>	9 Kg/mq
<b>Humidity</b>	10%+ / -2%
<b>Hardness</b>	35 N/mm <sup>2</sup>

\*Multi-width: from 3 to 5 mixed types of width, according to quality and availability

